



## Selection & Specification Data

<b>Product Name</b>	LizardSkin Ceramic Insulation
<b>Base</b>	Water-based Acrylic Insulation Coating
<b>Gloss</b>	Flat
<b>Color</b>	Black, White
<b>Wet Weight</b>	5.59 lbs./gallon
<b>Volume Solids Content</b>	70.6%
<b>Average Coat Thickness</b>	20-22 mils WFT at 70°-130°F – High Pass
<b>Practical Wet Coat Coverage</b>	50 ft <sup>2</sup> /gal @ 20 mils DFT
<b>VOC Content</b>	0.07 lbs/gal
<b>Weight DFT</b>	0.06 lbs / sq ft at 20 mils dft 0.27 kg / sq meter at 0.50 mm dft
<b>Limitations</b>	Applications should not exceed 350°F (176°C).
<b>Storage</b>	Do not subject wet coating in pail format to freezing conditions. Coating should be kept in a warehouse between 60°F and 90°F.

## Substrates & Surface Preparation

<b>Surface Prep</b>	Surface should be dry and free of foreign matter. Surface prep can be used to NACE 1-3 (SSPC SP 5-6) when applicable.
<b>Ferrous Surfaces</b>	Should be primed prior to application of LizardSkin Ceramic Insulation.
<b>Non-ferrous Surfaces</b>	The coating can be applied directly to non-ferrous surfaces. Surface should be clean and free of any oil, dirt or other foreign matter.

## Mixing & Thinning

<b>Mixing</b>	Only the paddle supplied in the Small Application Kit should be used. Use 3/8" – 1/2" drill motor to stir contents with paddle. .
<b>Thinning</b>	Thinning is normally not needed. Please consult LizardSkin for specific instructions if thinning is desired.
<b>Pot life</b>	Coating is one part, so no catalyzation is needed. Pail can be reused if properly sealed.
<b>Containers</b>	1 and 2 gallon pails

## Application Equipment

<b>Small Spray Application</b>	Please consult LizardSkin for the SuperPro Application Kit.
--------------------------------	---

## Application

<b>Substrate</b>	Substrate must be above 60°F during and after application for coating to dry properly.
<b>Estimated Dry Time</b>	1 hour and 15 min @ 77°F and 47% Relative Humidity @ 20 mils (low pass). Allow 24 hours for full cure at 70°F.
<b>Applying with LS SC</b>	If applying both LizardSkin Ceramic Insulation and LizardSkin Sound Control, Sound Control must be applied to the substrate prior to the Ceramic Insulation for both coatings to work to their full potential.
<b>Forced Drying</b>	Forced drying with heat directly over the surface is not recommended. This will prematurely skin the coating and cause improper drying. Elevating the surface temperature of the substrate prior to application will aid in dry times, but keep below 120°F.
<b>Environment Application Conditions</b>	It is recommended to apply this coating in an area that is above at least 75°F. High humidity areas will increase dry times. Forced ventilation is recommended as this help to evacuate water content out of the film. It is important to bring in air as well as exhaust air for best environmental conditions.
<b>Storage</b>	LizardSkin Ceramic Insulation should be kept in a storage area above 60°F or above. Product can be reused if sealed correctly. It is best to keep container out of direct sunlight for sustained periods of time.
<b>Shelf Life</b>	One year shelf life from date of manufacture.
<b>Caution</b>	Do not let product freeze.

## Cleanup and Safety

<b>Cleanup</b>	Equipment may be cleaned with soap & water
<b>Safety</b>	Dust mask and eye protection recommended
<b>Ventilation</b>	Recommended for constricted areas
<b>Caution</b>	This material is not for human consumption
<b>Clothing</b>	Coveralls or an apron & gloves are recommended *See MSDS sheet for further information on safety recommendations

## Company Information

<b>Contact Information</b>	LizardSkin Spray-on Insulation 4310 Campbell Rd. Houston, TX 77041 800-549-0042 www.lizardskin.com
----------------------------	--



LSCI 0611