

# ACRYLITHANE™ 2.8

## Acrylic Urethane Catalyzed Coating



### Technical Data

#### PRODUCT DESCRIPTION

A high performance, two component coating for use where appearance, durability, color and gloss retention plus chemical and corrosion resistance are paramount. For use on automobiles, trucks, trailers, railway cars, service stations, bulk tanks or chemical (acid or caustic) trailers.

For best results, use one of the JONES-BLAIR™ engineered systems for a total coating system.

#### FEATURES

- Same hardener as UREPRIME® 2.8 primer
- Excellent color retention
- Solvent resistant
- Chemical resistant
- Excellent gloss retention
- Lead and Chromate free
- Low VOC

#### PRODUCT DATA

Description	Results
Vehicle Type	Acrylic Polyester Urethane
Colors	Available in a variety of colors.
Gloss	Full
VOC (mixed)	336 g/L (2.8 lbs/gal)
Weight/Gallon (mixed)	10.7 pounds
Solids by Weight (mixed)	65.7%
Solids by Volume (mixed)	53.4% (Theoretical)
Viscosity (mixed)	30-35" / Zahn 3
Flash Point (white)	4°F
Dry Heat Resistance	300°F (149°C)
Freight Classification	See MSDS
Packaging	1 Gallon (mixed unit)

#### APPLICATION DATA

Description	Results
Application	Spray
Mix Ratio	3:1 by Volume
Catalyst	99955
Recommended Thickness	1.5 - 3.0 mils DFT
Dry Time @ 77°F, 50% RH	
No Accelerator	
Recoat	3 hours
Tack Free	4 hours
Handle	6 hours
With 1 fl oz/gal 99011	
Recoat	2 hours
Tack Free	2 hours
Handle	5 hours
Pot Life @75°F, 50% RH	
No Accelerator	
2X Viscosity	4 hours
Gel Time	8 hours
With 1 fl oz/gal 99011	
2X Viscosity	2 hours
Gel Time	4 hours
Coverage	571 sf/gal at 1.5 mils DFT

Thinner	21102 (See thinning instructions)
	21092 (See thinning instructions)
	21093 up to 3%
Clean Up	21092

The technical specifications for this data sheet are based on product 4700-003 White.

#### CURED FILM PERFORMANCE

Description	Test Method	Results
Q-UV A 340 (3,000 hrs)	ASTM D4587	> 95% gloss retention (60°) color change DE < .5
Xenon Arc (1,000 Hrs) quartz borosilicate filters	ASTM G147-96	> 95% gloss retention (60°)
Exterior Exposure 45° South Dallas, Texas	ASTM D1014	> 90% gloss retention, 3 Years
24 Hour Chemical Resistance Exposure (No Effect)	ASTM 1308	DI Water, 10% H <sub>2</sub> SO <sub>4</sub> , 10% NaOH, 25% H <sub>3</sub> PO <sub>4</sub> , 10% Acetic Acid, Xylene & Mineral Spirits
Impact Resistance	ASTM D2794	50 F & 20 R
Hardness	ASTM D3363	2H

#### EQUIPMENT RECOMMENDATIONS

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

**SPRAY APPLICATION (General):** The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

#### AIR ATOMIZED SPRAY:

	Model	Air Cap	Fluid Tip	Fluid Delivery	Atomizing Pressure
Pressure	Binks #18	63 pb	66	20 oz/min	50 - 55 psi
Pressure	DeVilbiss MBC-510	704	fx	20 oz/min	50 - 55 psi

#### AIRLESS SPRAY: NOT RECOMMENDED

#### GENERAL SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, dirt, grease, wax, mildew, loose or flaking paint and other surface contaminants. Remove loose, peeling, flaking or scaling paint and rust by scraping, sanding or wire brush or blasting.

For best results, an SSPC-SP 5 (NACE No. 1) white metal blast is minimum for severe exposure. For moderately severe (non-immersion) exposures an SSPC-SP 6 (NACE No. 3) commercial blast can be used.

#### DIRECTIONS FOR USE

**TINTING:** May be tinted with HS tint colors only.

**THINNING:** This product has been formulated to be applied without the need for additional thinning. However, application with certain equipment and under certain various conditions may be enhanced by reduction with thinners specified. Please note that additional reduction will increase VOC content of the mixed coating. Always know VOC restrictions for coatings applications in your area. This product and other referenced products may not meet VOC restrictions for your application and may not be available in your area.

**APPLICATION:** Mix thoroughly before use. Add 1 quart of 99955 per ¾ gallon unit of ACRYLITHANE™ 2.8 and mix thoroughly again. Only apply when air and surface temperature are between 40° – 100°F (7° - 38°C) and when the surface temperature is at least 5°F or 3°C above the dew point.

**DRYING TIME:** See application data for typical dry times. Low temperature, high humidity, poor ventilation and thick films will retard drying. Accelerator 99011 may be added at the rate of up to 1 fl oz per mixed gallon of ACRYLITHANE™ 2.8 to reduce the drying time.

**CLEAN UP:** Flush mixed material from pot and lines immediately after use. Clean up paint tools or spills immediately with recommended thinner, carefully observing cautions on paint and thinner labels. Dried paint may be removed by scraping.

## ENGINEERED SYSTEMS

### SYSTEM - A

For maximum corrosion resistance and durability. Recommended for use in coastal and marine exposures above the splash zone over a sandblasted surface.

**First Coat Primer:** 3 dry mils of 33910 CHEM-O-Z™ II Organic Zinc Rich Primer.

**Second Intermediate Coat:** 2 - 4 dry mils of UREPRIME® 2.8 Primer.

**Topcoat:** 3 dry mils of ACRYLITHANE™ 2.8 in the desired color for the finish coat.

**Clearcoat:** 1 - 2 dry mil of 4700-001 ACRYLITHANE™ 2.8 Clear (optional for ultimate gloss and durability).

### SYSTEM - B

For maximum chemical resistance while affording excellent corrosion resistance and durability in non-salt atmospheres. Recommended for use in inland areas and for resistance to acid and alkali. Sandblasting is recommended.

**First Coat Primer:** 2 - 4 dry mils of UREPRIME® 2.8 Primer.

**Topcoat:** 3 dry mils of ACRYLITHANE™ 2.8 in the desired color for the finish coat.

**Clearcoat:** 1 - 2 dry mil of 4700-001 ACRYLITHANE™ 2.8 Clear (optional for ultimate gloss and durability).

## HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 08092013 Acrylithane28TD.indd

**JONES-BLAIR®/NEOGARD®**

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 350-7624 - www.jones-blair.com - www.neogard.com